



ITEM	TEST DATA	
Fibre composition	50% viscose	
	50% polyester	
Bonding method	Needle punch on fibre web	
Mass per unit area	145g/m <sup>2</sup>	
<b>Breaking strength, N, min machine direction (MD), dry, wet cross direction (CD), dry, wet:</b>		
	Dry MD breaking strength ≥ 90 (N/5CM)	111.7 N/5CM
	Dry CD breaking strength ≥ 75 (N/5CM)	98.5 N/5CM
	Wet MD breaking strength ≥ 75 (N/5CM)	80.7 N/5CM
	Wet MD breaking strength ≥ 90 (N/5CM)	65.2 N/5CM
Absorbency	Absorbent ≥ 400 (%)	
		Dry weight: 4.77g
		Wet weight: 22.35g
		22.35/4.77 = 4.69 (469%)
		469% > 400%
Available colours	Blue (CLNP-1002)	
	Green (CLNP-1003)	
	Red (CLNP-1004)	
	Yellow (CLNP-1005)	

REVISION DATE: 23-06-2015



Cape Town  
Tel: 021 511 7250  
Fax: 021 511 7251

Johannesburg  
Tel: 011 902 3340  
Fax: 011 902 9437

Port Elizabeth  
Tel: 041 582 1624  
Fax: 041 581 0562

Durban  
Tel: 031 705 2752  
Fax: 086 566 5414

